

SILICON BRASS AND BRONZE C87200

CDA NUMBER	C87200	
Common Name	12A, Everdur	
COMPOSITION PERCENT	Min	Max
Copper (Cu)	89	
Tin (Sn)		1
Lead (Pb)		0.5
Zinc (Zn)		5
Iron (Fe)		2.5
Antimony (SB)		8
Nickel (Ni)		
Sulphur (S)		
Phosphorous (P)		
Aluminum (Al)		1.5
Manganese (Mn)		1.5
Silicon (Si)	1	5
Other (Total)		
NEAREST APPLICABLE CASTING STANDARDS		
ASTM (B Series)	B584	
SAE (J Series)	J462	
Federal (QQ-C- Series)	390	
Military (Mil-C- Series)	22229	
TYPICAL PROPERTIES	Typ	Min
Tensile Strength (ksi)	55	45
Yield Strength (.5% extension under load) (ksi)	25	18
Elongation (2 inch gauge length) (%)	30	20
Reduction of Area (%)		
Proportional Limit (ksi)		
Modulus of Elasticity (ksi)	15000	
Hardness (Brinell) (HB @ 3000kg)	85	
Machinability (% of free cutting brass)	40	
Fatigue Strength (10 ⁸ cycles) (ksi)		
Impact Strength (Charpy) (ft-lb)		
Impact Strength (Izod) (ft-lb)	33	
Shear Strength (ksi)	28	
Compressive Strength (0.001 in. set/in.) (ksi)	18	
Compressive Strength (0.010 in. set/in.) (ksi)	60	
Compressive Strength (0.100 in. set/in.) (ksi)		
Creep Strength (0.00001% per hour) (ksi)		
Melting Range (Liquidus-Solidus)(F)	1580-1780	
Coefficient of Thermal Expansion (per F @ 68-400F)		
Thermal Conductivity (Btu/sq.ft./ft./hr/F @ 68F)	16.4	
Specific Heat (Btu/lb/F @ 68F)	0.09	
Electrical Conductivity (% IACS @ 68F)	6	
Density (lb/cu.in. @ 68F)	0.302	
Pouring Temperature (Light Castings) (F)		
Pouring Temperature (Heavy Castings) (F)		
Patternmakers Shrinkage (in/ft)	1/4	
Drossing	Low	
Gassing	High	
Fluidity	High	
Corrosion Resistance: Excellent, especially to atmospheric corrosion.		
Applications: Bearings, bells, impellers, marine fittings, pump parts, statuary, valve stems, rocker arms, small boat propellers. These are the most popular alloys for artwork because of their high fluidity.		

Always use the design principles outlined on page two of this information sheet or at our website.

Consult your foundry early in the design process.

St. Paul Brass and Aluminum does not currently pour this alloy, but will consider it if purchased volumes justify the inventory.



St. Paul
Brass and Aluminum
Foundry